

## DYNACOLL® S 1252

45.13.083e / 05.11

### General Description

Saturated, linear copolyester, partially crystalline.

### Application

Thermoplastic hotmelt adhesives for fabrics and technical textile lamination e.g. for clothes or automotive interiors. Direct extrusion or preparation of adhesive films, nets and webs.

### Supply Form / Packaging

Granules in 25 kg paper-bags, aluminium laminated or in big-bags.

### Specification

Property	Value	Unit	Test method
Viscosity number	89 - 97	cm <sup>3</sup> /g	DIN 53 728
Glass transition temperature (DSC) <sup>1)</sup>	16 - 23	°C	DIN 53 765

### Typical data

Softening point (Ring & Ball)	135	°C	DIN ISO 4625
Melt flow rate 180 °C (MFR)	20	g/10 min	DIN ISO 1133 (21.6 N)
Melt viscosity 180 °C	360	Pa s	(Plate/Plate)
Open time	5	s	Degussa-method
Tensile strength	20	N/mm <sup>2</sup>	DIN EN ISO 527-1/3
Density	1.3	g/cm <sup>3</sup>	DIN 53 479

<sup>1)</sup> Differential scanning calorimetry

### Solubility

Most solvents: practically insoluble, soluble in methylene chloride.

## Storage Stability

Excluding sunlight and humidity S 1252 is stable at storage temperatures below 25 °C for at least 12 months.

## Safety and Handling

Please refer to our Safety Data Sheet.

---

### Evonik Operations GmbH

Paul-Baumann-Str. 1  
45764 Marl  
Germany  
PHONE +49 2365 49-02  
FAX +49 2365 49-5030

### Evonik Corporation

Resource Efficiency  
299 Jefferson Road  
Parsippany, NJ 07054-0677, USA  
PHONE +1 973 929-8000  
FAX +1 973 929-8460

### Evonik Degussa (China) Co. Ltd.

Resource Efficiency  
55 Chundong Rd., Xinzhuang Ind. Park  
Shanghai 201108, P.R. China  
PHONE +86 21 61191-027  
FAX +86 21 61191-254

Email [adhesives@evonik.com](mailto:adhesives@evonik.com)  
[www.evonik.com/adhesives-sealants](http://www.evonik.com/adhesives-sealants)  
[www.evonik.com/designed-polymers](http://www.evonik.com/designed-polymers)

Replaces leaflet 45.13.083e / 07.01 and all former issues  
Marl, May 13, 2011

DYNACOLL® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.