

VESTOPLAST® 308

34.13.074e / 14.07

Data sheet

| Property | Value | Unit | Test method |
|---|-------|-----------------|-----------------------------|
| Melt viscosity at 190 °C Rotational viscometer | 8000 | ± 2000 mPa s | according to DIN 53 019 |
| Softening point Ring and ball | 136 | ± 6 °C | according to DIN EN 1427 |
| Needle penetration (100/25/5) | 17 | ± 3 0.1 mm | according to DIN EN 1426 |

Special properties

VESTOPLAST 308 is a functionalized grade.

Application

Raw material for the production of hot melts for bonding metal and polar substrates.

Evonik Operations GmbH
Paul-Baumann-Str. 1
45772 Marl
Germany
PHONE +49 2365 49-02
FAX +49 2365 49-5030

Evonik Corporation
Resource Efficiency
299 Jefferson Road
Parsippany, NJ 07054-0677, USA
PHONE +1 973 929-8000
FAX +1 973 929-8460

E-Mail adhesives@evonik.com
www.evonik.com/adhesives-sealants
www.evonik.com/designed-polymers

Marl, July 04, 2014

VESTOPLAST® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.