

VESTOPLAST® 750

34.13.083e / 14.07

Data sheet

Property	Value		Unit	Test method
Melt viscosity at 190 °C Rotational viscometer	50000	± 10000	mPa s	according to DIN 53 019
Softening point Ring and ball	107	± 4	°C	according to DIN EN 1427
Needle penetration (100/25/5)	14	± 3	0.1 mm	according to DIN EN 1426

Special properties

VESTOPLAST 750 shows a good tear strength and elongation at break combined with a relatively low softening point.

Application

Raw material for the production of hot melt adhesives for the hygienic and woodworking industry.

Evonik Operations GmbH

Paul-Baumann-Str. 1
45772 Marl
Germany
PHONE +49 2365 49-02
FAX +49 2365 49-5030

Evonik Corporation

Resource Efficiency
299 Jefferson Road
Parsippany, NJ 07054-0677, USA
PHONE +1 973 929-8000
FAX +1 973 929-8460

E-Mail adhesives@evonik.com
www.evonik.com/adhesives-sealants
www.evonik.com/designed-polymers

Marl, July 11, 2014

VESTOPLAST® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.