

## VESTOPLAST® 792

34.13.085e / 14.07

### Data sheet

Property	Value	Unit	Test method
Melt viscosity at 190 °C Rotational viscometer	120000	± 30000 mPa s	according to DIN 53 019
Softening point Ring and ball	108	± 4 °C	according to DIN EN 1427
Needle penetration (100/25/5)	14	± 3 0.1 mm	according to DIN EN 1426

### Special properties

VESTOPLAST 792 is a high viscous grade of good tear strength and elongation at break.

### Application

Raw material for the production of hot melt adhesives for the furniture industry.

**Evonik Operations GmbH**  
Paul-Baumann-Str. 1  
45772 Marl  
Germany  
PHONE +49 2365 49-02  
FAX +49 2365 49-5030

**Evonik Corporation**  
Resource Efficiency  
299 Jefferson Road  
Parsippany, NJ 07054-0677, USA  
PHONE +1 973 929-8000  
FAX +1 973 929-8460

E-Mail [adhesives@evonik.com](mailto:adhesives@evonik.com)  
[www.evonik.com/adhesives-sealants](http://www.evonik.com/adhesives-sealants)  
[www.evonik.com/designed-polymers](http://www.evonik.com/designed-polymers)

Marl, July 17, 2014

VESTOPLAST® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.