

## Shell GTL Sarawax SX 105

### non-functionalised Fischer-Tropsch hard paraffin

34.13.170e / 2020.11

#### Data sheet

Property	Value	Unit	Test method
Drop point	114 - 120	°C	DGF M-III 3
Penetration (needle)	1	mm · 10 <sup>-1</sup>	DGF M-III 9b
Viscosity at 130 °C	< 20	mPa s	DIN 52 007/2
Acid number	< 1	mg KOH/g	DGF M-IV 2
Saponification number	< 1	mg KOH/g	DGF M-IV 2
Color	white		
Supply form	prills		

**Evonik Corporation**  
Resource Efficiency  
299 Jefferson Road  
Parsippany, NJ 07054-0677, USA  
PHONE +1 973 929-8000  
FAX +1 973 929-8460

**Evonik Resource Efficiency GmbH**  
Paul-Baumann-Str. 1  
45772 Marl,  
GERMANY  
PHONE +49 2365 49-02  
FAX +49 2365 49-5030

E-Mail [adhesives@evonik.com](mailto:adhesives@evonik.com)

[www.evonik.com/adhesives-sealants](http://www.evonik.com/adhesives-sealants)  
[www.evonik.com/designed-polymers](http://www.evonik.com/designed-polymers)

Marl, November 02, 2020

VESTOWAX® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.