

Product information

POLYVEST[®] EP ST-E 60

Experimental Product (EP)

TRIETHOXYSILANE-TERMINATED LIQUID POLYBUTADIENE

GENERAL DESCRIPTION

POLYVEST[®] EP ST-E 60 is a stereospecific, low viscous and triethoxysilane-terminated liquid polybutadiene having the following composition of double bonds:

- 1,2-vinyl double bonds approx. 22 %
- 1,4-trans double bonds approx. 58 %
- 1,4-cis double bonds approx. 20 %

SPECIFICATION

Property	Value	Unit	Test Method
Viscosity at 20°C	7,500 – 15,000	mPa s	DIN EN ISO 3219
Viscosity at 30°C	4,000 – 7,500	mPa s	DIN EN ISO 3219
Gardner Color	≤ 1.5		DIN EN ISO 4630
Water Content	≤ 500	mg/kg	DIN 51 777-2

TYPICAL DATA

Property	Value	Unit	Test Method
Density at 25°C	0.8 - 1.0	g/cm ³	DIN 51757, method 4
Mean Molar Mass	approx. 3,200	g/mol	GPC* (polybutadiene standard)
Glass Transition Temperature (T _g)	approx. -80	°C	DIN EN ISO 11 357-1
Silane functionality	approx. 1.5		calculated
Residue on Ignition at 950°C	1.0 - 3.5	wt%	ASTM D 6740

*GPC: gel permeation chromatography

GENERAL USE AND APPLICATIONS

Due to its unsaturated polymer backbone and the terminal triethoxysilane functionalities, the apolar and hydrophobic hydrocarbon resin POLYVEST® EP ST-E 60 is a highly reactive binder with very good dispersing properties of inorganic fillers. POLYVEST® EP ST-E 60 exhibits the following features:

- Excellent compatible with solid rubber and recycled rubber
- high chemical resistance
- good dispersion and chemical modification with high loading capacity of inorganic fillers
- high cold resistance by keeping good flexibility at low temperatures
- good solubility in aliphatics, aromatics and ethers
- low moisture and gas permeability
- possibility of moisture induced curing

POLYVEST® EP ST-E 60 is used in various fields of application such as:

- additive for tires
- adhesive and sealants
- insulated glass sealants
- waterproofing membranes and coatings
- dispersion additive for rubber based formulations

We are pleased to send guideline formulations.

SUPPLY FORM

Viscous liquid

PACKAGING AND TRANSPORT

- steel drums (content 180 kg)
- IBC (content 850 kg)

STORAGE

POLYVEST® EP ST-E 60 is stable for at least 12 months with exclusion from air, light and moisture at storage temperatures below 25°C.

SAFETY AND HANDLING

POLYVEST® EP ST-E 60 is supplied under a blanket of inert gas (nitrogen). The contact with air oxygen should be avoided as possible. Opened containers should be blanketed with inert gas again and closed tightly.

We are pleased to send our current Material Safety Data Sheet.

Marl, October 12, 2018; This data sheet replaces all former issues.

POLYVEST® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Coating & Adhesive Resins
Paul-Baumann-Str. 1
45764 Marl
Germany

EVONIK CORPORATION

Coating & Adhesive Resins
299 Jefferson Road,
Parsippany, NJ 07054-0677
USA

**EVONIK SPECIALITY CHEMICALS
(SHANGHAI) CO., LTD.**

55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
P.R. China

For contacts in your country, please visit: www.evonik.com/adhesive-resins-contact
E-mail: adhesives@evonik.com
www.evonik.com/designed-polymers

